



Aculon® NanoProof™ 3.5

Hydrophobic coating

Aculon® NanoProof™ 3.5 repellency product is a surface treatment capable of imparting hydrophobicity to printed circuit boards and electronic components in a simple, one-step process. Aculon® NanoProof™ 3.5 is typically applied by dipping, flow coating or spraying and result in hydrophobic films that allow post application, push-through electrical connection.

Solids	Solvent	Color
<25% Proprietary Ingredient	Hydrocarbon Solvent	Clear liquid

Physical Properties of Formulation (all values @ 25°C)	
Viscosity*	< 25 cP
Boiling Point of Solvent	93.3-104.4°C
Flash Point	-11°C
Environmental	Nontoxic, non-ozone depleting, flammable
Shelf Life	2 Years (Unopened container)
Specific Gravity	0.7 – 0.8 g/ml

*Determined by Zahn Cup #1 testing

Physical Properties of Post Treatment Coating	
Coating Thickness (varies with application)	10 – 30 microns
Visible Light Transmission	90%
Water Contact Angle	> 100°
Oil Contact Angle	< 20°

Features

- IPX-7 protection of electronic circuits
- Provides a hydrophobic film
- Films allow push-through electrical connection
- Easy to apply
- Adhesion to a broad range of substrates
- Coatings allow rework of PCB's
- Coating is non-conductive
- Contains a UV tracer
- No cure required

Application Ideas

- Water proofing of PCB's
- Protecting electronic devices from exposure to common liquids

Application Techniques

Surface Preparation/ Cleaning:

Ensure that the surface is free of any grease, fingerprints, adhesive residues or dirt. This can be accomplished by first degreasing the surface with solvents or by rinsing with soap and water or by rinsing with IPA. Depending on the sensitivity of your part to liquids Kyzen cleaners like Ionox I3416 or Cybersolv 141-R may be most appropriate for removing surface contamination.

Contact Aculon if you are unsure what cleaner to use and we will recommend one best suited for your application. Substrates should be coated after cleaning as soon as possible to minimize the potential for recontamination.

Treatment Application:

Dispense: Dispense product over the surface. Apply enough material to coat the surface. Allow excess material to drain.

Spray: Spray the solution on the substrate, air dry. If the coating is too thick, reduce the amount applied by changing the settings on the spray gun or request a sample of diluent from Aculon. Spray Equipment Suggestions; PVA FCS300 Front Closing Spray Valve, typically used settings are 40 psi main pressure, 8 psi coating pressure, 12 psi atomization pressure, micrometer = 10, 6" distance to part being coated, and one double pass with the sprayer.

Dip: Immerse the substrate in the solution for 20 seconds, air dry till solvent evaporated. Recommended dip containers are stainless steel, glass or aluminum. Plastic containers are likely to contaminate the coating solution reducing performance.

Drying: Allow the film to set at room temperature until the solvent has evaporated. Once dried the gel like film remains physically deformable, thus care should be taken when handling the part so as to not disturb the coating in sensitive areas. In some cases additional thermal treatment (e.g. 100°C for 5 minutes) will speed solvent evaporation.

Testing For Hydrophobicity:

Allow droplets of water to fall onto the surface, they should bead up to a contact angle >90°. If the surface is not hydrophobic clean the surface again and reapply.

Safety, Handling, Storage, Shelf Life:

Store in a cool (~25°C) and dry area, and keep away from direct sun light. See this product's MSDS for proper handling. When stored properly, product has a 2 year shelf life.

For Additional Information:

To request additional product information or sales assistance, contact Aculon's Technical Team, at 858-350-9474. For information on other Aculon products, please visit our website at www.aculon.com.

Product Use: All statements, technical information and recommendations contained in this document are based on tests or experience that Aculon believes to be dependable. However, many factors beyond Aculon's control can affect the use and effectiveness of an Aculon product in a particular use or application, including conditions under which the product is used and the time and conditions in which the product is expected to perform. Since these factors are exclusively within the user's knowledge and control, it is essential that the user evaluate the Aculon product to determine whether it is fit for a specific purpose and suitable for the user's method of application.

Warranty and Liability: Aculon makes no warranty or representation, expressed or implied, by operation of law or otherwise, as to the merchantability or fitness for a particular purpose of the goods arising out of a course of dealing, custom or usage of trade. Aculon shall not be liable for any defect in the goods sold hereunder and customer releases Aculon from any and all liability for negligence. Aculon will not be liable for consequential, incidental or any damages other than repair or replacement of defective good or refund of the purchase price paid for such defective goods.

Aculon • 11839 Sorrento Valley Road, Suite 901 • San Diego • California • 92121
• Tel: 858-350-9474 • Email: info@aculon.com

