

OPTOLINQ™ GT-W170-2



White reflective compound

- Oxidation resistance
- 92% Reflectance at 940nm
- 93% Reflectance at 800nm

OPTOLINQ GT-W170-2 is a white reflective compound used in optocoupler, photocoupler applications. It exhibits excellent reflectance and transmittance at 800 and 940nm and displays high whiteness and oxidation resistance. This formulation contains ~70-75% crushed silica and performs great against shrinkage and stress.

Recommended Curing Schedule: 150 - 200sec + 2 - 6 hours @150°C

Formulation

Property	Value
Epoxy	Multifunctional + BPA
Hardener	Anhydride
Filler Type	Crushed
Filler content	70 - 75%

Molding Parameters

Molding Condition	Value	Unit
Preheat Temperature	70 - 90	°C
Mold Temperature	170 - 180	°C
Transfer pressure	30 - 60	kgf/cm2
Transfer time	20 - 50	sec

Cured properties

Property	Value	Unit	Condition
Specific Gravity	1.85	-	-
Spiral flow	30 - 60	Inch	@175°C
Gel Time	20 - 40	Sec	@175°C
Glass transition temperature	150	°C	-
CTE α1	19 - 22	ppm/°C	-
CTE α2	40 - 70	ppm/°C	-
Flexural Strength @ 25°C	130	MPa	@ 25°C
Flexural Modulus @ 25°C	16	GPa	@ 25°C
Light Reflectance	>90	%	@800nm
Light Transmittance	<0.1	%	@800nm
pH	4	-	-
CTI	200	V	-
Dielectric Strength	12	kV/mm	@ 25°C

Storage and Handling

Store in a ventilated, dry, and clean environment below 5°C. Keep away from fire and heat sources. It is strictly forbidden to store in outdoor environments. At proper storage conditions, the product has a shelf life of 6 months.

Europe

Industrieweg 15E,
1566JN Assendelft
The Netherlands
Phone: +31 (20) 893 2224
Email: info@caplinq.com

Canada

80 Sirocco Crescent
Ottawa ON, K2S 2C9
Canada
Phone: +1 (613) 482-2215
Email: info@caplinq.com



United States

847 Sumpter Road #5155
Detroit, MI 48111
United states
+1 (313) 558-8243
Email: info@caplinq.com

Asia

Minle Garden, Baoan dst
Shenzhen City - 51831
China
Phone: +861368608 1428
Email: info@caplinq.com