




PEMION® FUEL CELL OFFERINGS

Hydrocarbon Proton Exchange Membranes & Polymers

**111-2386 East Mall
Vancouver, BC Canada
V6T 1Z3**



PRODUCT INFORMATION

Ionomr's advanced proton exchange membranes and polymers are a breakthrough in material science with a uniquely stable hydrocarbon structure, making it the only product of its kind.

Pemion® represents a fundamental shift in the approach to proton exchange technology through its migration from perfluorosulfonic acid (PFSA) chemistry to hydrocarbon materials, providing substantially lower gas crossover and helping address PFSA-related environmental and end-of-life issues at considerably higher performance.

Pemion® enables major efficiency and performance gains, while aligning with needs of the renewable economy. It is the only environmentally-friendly option on the market.

Produced on reinforcement at thicknesses competitive to leading PFSA membranes in the industry, Pemion® provides leading conductance and durability without compromise.

For use in fuel cell applications including heavy duty transport & automotive, hydrocarbon based Pemion® membrane and ionomer offers several advantages over incumbent perfluorinated materials to increase the efficiency, versatility, and lifetime of fuel cell engines, including: lower gas crossover for increases to range and the lifetimes of both membrane and catalyst; higher proton conductivity for additional gains to efficiency and power density; significantly greater temperature stability to enable many system design benefits such as higher fuel cell operating temperature; & a substantially easier end-of-life precious metal recovery, reducing costs & eliminating the environmental concerns specific to acidic perfluorinated compounds.

PEMION® REINFORCED MEMBRANES — PRE-PRODUCTION

Thickness and Basis Weight Properties

Membrane Type	Typical Thickness (μm)		Basis weight (g/m²)
PF1-HLF8-15-X	15		18
Physical Properties ¹	MD	TD	Test Method
Tensile Strength, MPa	> 50	> 50	ASTM 638
Young's Modulus, MPa	> 600	> 600	ASTM 638
Elongation to break	> 50%	> 50%	ASTM 638
Hydrolytic Properties ²			
Water Uptake, wt%:			ASTM D570
to water soaked, 22 °C	110 - 140%		
to water soaked, 80 °C	150 - 190%		
Linear Expansion			ASTM D570
to water soaked, 22 °C	< 7%		
to water soaked, 80 °C	< 11%		
Z-Expansion			ASTM D570
to water soaked, 22 °C	< 140%		
to water soaked, 80 °C	< 190%		
Electrochemical Properties ³			
Area Resistance	< 42.5 mΩ • cm²		
Hydrogen Crossover Current	< 2.0 mA/cm²		Atmospheric
	< 6.0 mA/cm²		150 kPa gauge
Measured Ex-situ Conductivity ⁴	In-plane	Through-plane	
PF1-HLF8-15-X	> 100 mS/cm	> 90 mS/cm	
Reference:	In-plane	Through-plane	
NR211	60 ± 5 mS/cm	60 ± 5 mS/cm	
15 μm Reinforced PFSA	65 ± 5 mS/cm	44 ± 4 mS/cm	
Other Properties			
Specific Gravity	1.3 g/cm³		
Maximum Processing Temperature	160 °C		
Maximum Fuel Cell Operating Temperature	110 °C		
Polymer Tg	> 300 °C		

Note: These materials are only intended to be used for early development activities and not intended for production items. Product information is to be used as a guide (reference data) only, and not as a design specification. Product information is subject to change at any time as part of ongoing product development. Ionomr makes no warranties, express or implied, and assumes no obligation or liability in connection with any use of this information or for results obtained in reliance thereon.

¹ Membranes equilibrated at 22 °C under atmospheric condition for 24 h prior to measurement.

² Measured from dried to fully equilibrated in de-ionized water, at the specified temperatures.

³ Measured *in-situ* via chronoamperometry at 80 °C, 100/100% RH (anode/cathode).

⁴ Membranes equilibrated in de-ionized water at 22 °C for 24 h prior to measurement. Measured *ex-situ* using electrochemical impedance spectroscopy. Pemion and reference membranes measured under identical conditions.

PEMION® IONOMERS: DRY RESIN

Ionomer Type	IEC ¹ (meq/g)	EW (g/eq.)	Density (g/cm ³)	Solubility ²
PP1-HNN8-00	2.8 - 3.1	320 - 360	1.2	Alcohols and alcohol/water mixtures
Ionomer Type	IEC ¹ (meq/g)	EW (g/eq.)	Density (g/cm ³)	Solubility
Long side-chain PFSA	0.9 - 1.0	1000 - 1,100	2.0	Alcohols and alcohol/water mixtures
Short side-chain PFSA	1.1 - 1.3	770 - 910	2.0	Alcohols and alcohol/water mixtures
Notes				

¹ IEC of polymer powder measured as-received.

² Refer to FM-7013 for additional information.

These are prototype materials only intended to be used for early development activities and not intended for production items. Product information is to be used as a guide only, subject to change at any time.

Document ID	Title
-------------	-------

FM-6027-E	Properties of Pemion® Hydrocarbon Proton Exchange Membrane
-----------	--

Revision	Prepared By	Approved By	Effective Date
----------	-------------	-------------	----------------

E	Mike Adamski	Andrew Belletti	Oct 4, 2022
---	--------------	-----------------	-------------

This document is reviewed to ensure its continuing relevance to the systems and process that it describes.

REVISION HISTORY:

Revision	Date	Description of Changes	Approved By
----------	------	------------------------	-------------

A	March 12, 2021	Initial Draft	Ben Britton
B	July 26, 2021	Added new picture, PF1-HLF9-15-X	Ben Britton
C	Sept. 24, 2021	Added PF1-HLF8-15-X	Ben Britton
D	March 2, 2021	General revisions	Andrew Belletti
E	Oct 2, 2022	PF1-HLF8-15-X properties updates, general revisions	Andrew Belletti