

LOCTITE ECCOBOND UF 3820

September 2018

PRODUCT DESCRIPTION

LOCTITE ECCOBOND UF 3820 provides the following product characteristics:

Technology	Epoxy
Appearance	Black liquid
Cure	Heat cure
Product Benefits	<ul style="list-style-type: none"> • High Tg • Easy rework • Halogen free • One component • Fast cure at moderate temperatures • Room temperature flow capability • High fracture toughness • Excellent thermal cycle performance • Compatible with most Pb-free solders • Stable electrical performance under thermal/humidity bias
Application	Underfill
Typical Package Application	CSP, WLCSP and BGA

LOCTITE ECCOBOND UF 3820 reworkable underfill is specially designed for CSP, WLCSP and BGA applications. It is formulated to cure quickly at moderate temperatures to minimize stress to other components. This material's high glass transition temperature and high fracture toughness enables excellent protection of solder joints during thermal cycling.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield CP50-1, 25 °C, mPa·s (cP):	
@ Shear rate of 1,000 s ⁻¹	340
Thixotropic Index	1.1
Specific Gravity, Pycnometer, g/ml	1.24
Work Life @ 25°C, 25% change in viscosity, day	1
Shelf Life, days:	
@ -40°C	180
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE

Cure Schedule

10 minutes @ 130°C

Alternate Cure Schedule

5 minutes @ 150°C or

3 minutes @ 160°C

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Glass Transition Temperature (Tg) by TMA, °C	133
Coefficient of Thermal Expansion, , TMA:	
Below Tg, ppm/°C	51
Above Tg, ppm/°C	172
Storage Modulus, DMA:	
@ 25°C	N/mm ² 2,560 (psi) (371,300)
@ 100°C	N/mm ² 2,070 (psi) (300,230)
@ 150°C	N/mm ² 50 (psi) (7,105)
@ 200°C	N/mm ² 25 (psi) (3,625)
Fracture Toughness K1c, Instron, MPa(m ^{1/2})	1.5

Electrical Properties

Dielectric Constant / Dissipation Factor:	
@ 850 MHz	2.94/0.048
@ 1575 MHz	3.02/0.052
@ 2500 MHz	2.96/0.047
@ 5000 MHz	2.93/0.052

TYPICAL PERFORMANCE OF CURED MATERIAL

Shear Strength

PCB to PCB	N/mm ² 10.9 (psi) (1,581)
------------	---

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

THAWING:

1. Allow container to reach room temperature before use.
2. After removing from the freezer, set the syringes to stand vertically while thawing.
3. DO NOT open the container before contents reach 25°C temperature. Any moisture that collects on the thawed container should be removed prior to opening the container.
4. DO NOT re-freeze. Once thawed to 25°C, the adhesive should not be re-frozen.
5. Typical thaw times are listed as follows:
 - 1 hour for 10 cc syringes
 - 1.5 hours for 30 cc syringes
 - 4 to 5 hours for 6-ounce cartridges

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : -45 to -35 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb/F}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{psi} \times 145 = \text{N/mm}^2$

$\text{MPa} = \text{N/mm}^2$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel

Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 0.4

Americas
+1.888.943.6535

Europe
+32.1457.5611

Asia
+86.21.2891.8000

For the most direct access to local sales and technical support visit: www.henkel.com/electronics