

LINQBOND™ PM-1231



Two-component Epoxy Potting Material

- High resistance against weathering, aging, and UV radiation
- Non-corrosive, insulating, moisture-proof, and shock-resistant
- Solvent-free, environmentally friendly, and low in carbon footprint

LINQBOND™ PM-1231 is a two-component potting epoxy designed for casting, bonding, and sealing electronic components. It boasts outstanding aging and moisture resistance, excellent electrical insulation, high hardness, and a high breakdown voltage. Additionally, **PM-1231** offers exceptional weather, UV, and shock resistance, while remaining non-corrosive and environmentally friendly. **LINQBOND™ PM-1231** is well-suited for potting electronic components and modules that require high transparency, especially for potting digital tubes at room temperature.

Premixed properties

Property	Part A	Part B
Appearance	Transparent Liquid	Transparent Liquid
Viscosity	4000 cP	700 cP
Density	1.10 g/cm ³	1.00 g/cm ³
Shelf life	183 days	183 days

Mixed properties

Property	Value	Unit
Mixing ratio by Weight	2:1	–
Pot Life	0.5	h
Full Curing Time	48	h

Cured properties

Property	Value	Unit
Shore Hardness	80	Shore D
Linear Shrinkage Rate	0.8	%
Operating Temperature	–40 to 90	°C
Thermal Conductivity	0.3	W/m · K
Dielectric Strength	≥25	kV/mm
Volume Resistance	1.2×10 ²⁴	Ω · cm

Europe

Industrieweg 15E,
1566JN Assendelft
The Netherlands
Phone: +31 (20) 893 2224
Email: info@caplinq.com

Canada

80 Sirocco Crescent
Ottawa ON, K2S 2C9
Canada
Phone: +1 (613) 482-2215
Email: info@caplinq.com



North America

36927 Schoolcraft Rd
Livonia, MI 48150
United states
Phone: +1 (313) 558-8243
Email: info@caplinq.com

South East Asia

S-08-07 Persiaran Triangle
B Lepas, Penang 11900
Malaysia
Phone: +60(12)4302223
Email: info@caplinq.com

Processing Instructions

1. Before potting, make sure the surface is clean. Remove any oil or dust.
2. Mix component A and B according to specified ratio. Stir thoroughly to ensure uniformity while preventing air to be introduced into the mixture. Automatic mixing and filling machine can be used. Scrape the sides of the container to ensure even mixing until the color is consistent throughout.
3. Use the mixture within 30 minutes.
4. Allow the potted workpiece cure at room temperature until the surface is dry. Full curing typically occurs within 48 hours. The curing process is influenced by temperature variations; generally, higher temperatures result in faster curing, while lower temperatures lead to slower curing.

Precautions for Use

1. Before use, thoroughly mix Part A. Stratification may occur during long-term storage due to its high specific gravity. Mixing ensures consistent product performance. Do this in a well-ventilated area.
2. Use all of the mixed Part A and B at once. Seal and store any components for future use.
3. Typically, keep the potting thickness within 30mm. For deeper potting, contact the manufacturer for guidance.

Please note that the provided information is based on available data and typical conditions. For specific applications and detailed test results, refer to the actual test data and conduct appropriate certifications.

Storage and Handling

Store in a ventilated, dry, and clean environment at 3–10 °C. Keep away from fire and heat sources. It is strictly forbidden to store in outdoor environments. At proper storage conditions, Part A and Part B has a shelf life of 6 months. Shelf life can be extended by using cold storage.

Europe

Industrieweg 15E,
1566JN Assendelft
The Netherlands
Phone: +31 (20) 893 2224
Email: info@caplinq.com

Canada

80 Sirocco Crescent
Ottawa ON, K2S 2C9
Canada
Phone: +1 (613) 482-2215
Email: info@caplinq.com



North America

36927 Schoolcraft Rd
Livonia, MI 48150
United states
+1 (313) 558-8243
Email: info@caplinq.com

South East Asia

S-08-07 Persiaran Triangle
B Lepas, Penang 11900
Malaysia
Phone: +60(12)4302223
Email: info@caplinq.com