



Safety Data Sheet according to Regulation (EC) No 1907/2006

Page 1 of 19

LOCTITE 3508NH known as Hysol 3508NH 30ml EFD M/L

SDS No. : 377296
V002.0

Revision: 15.05.2019
printing date: 17.02.2020

Replaces version from: 06.06.2014

SECTION 1: Identification of the substance/mixture and of the company/undertaking

1.1. Product identifier

LOCTITE 3508NH known as Hysol 3508NH 30ml EFD M/L

1.2. Relevant identified uses of the substance or mixture and uses advised against

Intended use:
Adhesive

1.3. Details of the supplier of the safety data sheet

Henkel Ltd
Wood Lane End
HP2 4RQ Hemel Hempstead

Great Britain

Phone: +44 1442 278000
Fax-no.: +44 1442 278071

ua-productsafety.uk@henkel.com

1.4. Emergency telephone number

24 Hours Emergency Tel: +44 (0)1442 278497

SECTION 2: Hazards identification

2.1. Classification of the substance or mixture

Classification (CLP):

Skin irritation	Category 2
H315 Causes skin irritation.	
Serious eye irritation	Category 2
H319 Causes serious eye irritation.	
Skin sensitizer	Category 1
H317 May cause an allergic skin reaction.	
Chronic hazards to the aquatic environment	Category 2
H411 Toxic to aquatic life with long lasting effects.	

2.2. Label elements

Label elements (CLP):

Hazard pictogram:



Contains

reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight \leq 700)

Bisphenol F diglycidyl ether
Bisphenol-F epichlorhydrin resin; MW<700
1-Chloro-2,3-epoxypropane, polymer with polypropyleneglycol

Maleic anhydride

Signal word:	Warning
Hazard statement:	H315 Causes skin irritation. H317 May cause an allergic skin reaction. H319 Causes serious eye irritation. H411 Toxic to aquatic life with long lasting effects.
Precautionary statement: Prevention	P273 Avoid release to the environment. P280 Wear protective gloves.
Precautionary statement: Response	P302+P352 IF ON SKIN: Wash with plenty of soap and water. P333+P313 If skin irritation or rash occurs: Get medical advice/attention. P337+P313 If eye irritation persists: Get medical advice/attention.

2.3. Other hazards

Not fulfilling Persistent, Bioaccumulative and Toxic (PBT), very Persistent and very Bioaccumulative (vPvB) criteria.

SECTION 3: Composition/information on ingredients

3.2. Mixtures

General chemical description:

1-c- epoxide adhesive

Declaration of the ingredients according to CLP (EC) No 1272/2008:

Hazardous components CAS-No.	EC Number REACH-Reg No.	content	Classification
reaction product: bisphenol-A- (epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	01-2119456619-26	50- 100 %	Skin Irrit. 2 H315 Skin Sens. 1 H317 Eye Irrit. 2 H319 Aquatic Chronic 2 H411
Bisphenol F diglycidyl ether 39817-09-9	254-641-8	10- 20 %	Skin Irrit. 2; Dermal H315 Skin Sens. 1 H317 Eye Irrit. 2 H319 Aquatic Chronic 2 H411
Bisphenol-F epichlorhydrin resin; MW<700	01-2119454392-40	10- 20 %	Skin Irrit. 2; Dermal H315 Skin Sens. 1A H317 Aquatic Chronic 2 H411
1-Chloro-2,3-epoxypropane, polymer with polypropyleneglycol 9072-62-2		1- < 3 %	Eye Irrit. 2 H319 Skin Irrit. 2 H315 Skin Sens. 1 H317 Aquatic Chronic 3 H412
Maleic anhydride 108-31-6	203-571-6 01-2119472428-31	0,0001- < 0,01 % (1 ppm- < 100 ppm)	Resp. Sens. 1 H334 Skin Sens. 1A H317 Acute Tox. 4; Oral H302 STOT RE 1; Inhalation H372 Skin Corr. 1B H314 Eye Dam. 1 H318

For full text of the H - statements and other abbreviations see section 16 "Other information".
Substances without classification may have community workplace exposure limits available.

SECTION 4: First aid measures

4.1. Description of first aid measures

Inhalation:

Move to fresh air, consult doctor if complaint persists.

Skin contact:

Rinse with running water and soap.
Obtain medical attention if irritation persists.

Eye contact:

Rinse immediately with plenty of running water (for 10 minutes), seek medical attention from a specialist.

Ingestion:

Rinse mouth, drink 1-2 glasses of water, do not induce vomiting, consult a doctor.

4.2. Most important symptoms and effects, both acute and delayed

EYE: Irritation, conjunctivitis.

SKIN: Redness, inflammation.

SKIN: Rash, Urticaria.

4.3. Indication of any immediate medical attention and special treatment needed

See section: Description of first aid measures

SECTION 5: Firefighting measures**5.1. Extinguishing media****Suitable extinguishing media:**

Foam, extinguishing powder, carbon dioxide.

Fine water spray

Extinguishing media which must not be used for safety reasons:

High pressure waterjet

5.2. Special hazards arising from the substance or mixture

Danger of decomposition if exposed to heat.

The product may undergo spontaneous polymerization at high temperatures. Polymerization is exothermic and may cause damage to the container and/or release of thermal decomposition products.

See section 10.

5.3. Advice for firefighters

Wear self-contained breathing apparatus.

Additional information:

In case of fire, keep containers cool with water spray.

SECTION 6: Accidental release measures**6.1. Personal precautions, protective equipment and emergency procedures**

Avoid contact with skin and eyes.

Wear protective equipment.

Ensure adequate ventilation.

6.2. Environmental precautions

Do not empty into drains / surface water / ground water.

6.3. Methods and material for containment and cleaning up

Remove mechanically.

For small spills wipe up with paper towel and place in container for disposal.

For large spills absorb onto inert absorbent material and place in sealed container for disposal.

Dispose of contaminated material as waste according to Section 13.

6.4. Reference to other sections

See advice in section 8

SECTION 7: Handling and storage**7.1. Precautions for safe handling**

Ensure good ventilation/suction at the workplace.

Avoid skin and eye contact.

See advice in section 8

Avoid open flames.

Hygiene measures:

Wash hands before work breaks and after finishing work.

Do not eat, drink or smoke while working.

Good industrial hygiene practices should be observed.

7.2. Conditions for safe storage, including any incompatibilities

Store in sealed original container.

Store in a cool, dry place.

Ensure that storage and workrooms are adequately ventilated.

Must be stored in a room with spill collection facilities.

Keep away from heat and direct sunlight.

Refer to Technical Data Sheet

7.3. Specific end use(s)

Adhesive

SECTION 8: Exposure controls/personal protection**8.1. Control parameters****Occupational Exposure Limits**

Valid for
Great Britain

Ingredient [Regulated substance]	ppm	mg/m ³	Value type	Short term exposure limit category / Remarks	Regulatory list
Maleic anhydride 108-31-6 [MALEIC ANHYDRIDE]		3	Short Term Exposure Limit (STEL):		EH40 WEL
Maleic anhydride 108-31-6 [MALEIC ANHYDRIDE]		1	Time Weighted Average (TWA):		EH40 WEL

Occupational Exposure Limits

Valid for
Ireland

Ingredient [Regulated substance]	ppm	mg/m ³	Value type	Short term exposure limit category / Remarks	Regulatory list
Maleic anhydride 108-31-6 [MALEIC ANHYDRIDE]	0,01		Time Weighted Average (TWA):		IR_OEL

Predicted No-Effect Concentration (PNEC):

Name on list	Environmental Compartment	Exposure period	Value				Remarks
			mg/l	ppm	mg/kg	others	
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	aqua (freshwater)		0,006 mg/l				
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	aqua (marine water)		0,001 mg/l				
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	sewage treatment plant (STP)		10 mg/l				
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	sediment (freshwater)				0,996 mg/kg		
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	sediment (marine water)				0,1 mg/kg		
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	Soil				0,196 mg/kg		
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	oral				11 mg/kg		
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	aqua (intermittent releases)		0,018 mg/l				
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	aqua (freshwater)		0,003 mg/l				
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	aqua (marine water)		0,0003 mg/l				
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	sewage treatment plant (STP)		10 mg/l				
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	sediment (freshwater)				0,294 mg/kg		
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	sediment (marine water)				0,0294 mg/kg		
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	Soil				0,237 mg/kg		
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	aqua (intermittent releases)		0,0254 mg/l				
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	Air						
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	Predator						
Maleic anhydride 108-31-6	aqua (freshwater)		0,1 mg/l				

Maleic anhydride 108-31-6	aqua (marine water)		0,01 mg/l				
Maleic anhydride 108-31-6	aqua (intermittent releases)		0,4281 mg/l				
Maleic anhydride 108-31-6	Soil		0,0415 mg/l				
Maleic anhydride 108-31-6	sediment (freshwater)				0,334 mg/kg		
Maleic anhydride 108-31-6	sediment (marine water)				0,0334 mg/kg		
Maleic anhydride 108-31-6	sewage treatment plant (STP)		44,6 mg/l				

Derived No-Effect Level (DNEL):

Name on list	Application Area	Route of Exposure	Health Effect	Exposure Time	Value	Remarks
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	Workers	dermal	Acute/short term exposure - systemic effects		8,33 mg/kg	
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	Workers	Inhalation	Acute/short term exposure - systemic effects		12,25 mg/m3	
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	Workers	dermal	Long term exposure - systemic effects		8,33 mg/kg	
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	Workers	Inhalation	Long term exposure - systemic effects		12,25 mg/m3	
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	General population	dermal	Acute/short term exposure - systemic effects		3,571 mg/kg	
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	General population	dermal	Long term exposure - systemic effects		3,571 mg/kg	
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	General population	oral	Acute/short term exposure - systemic effects		0,75 mg/kg	
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	General population	oral	Long term exposure - systemic effects		0,75 mg/kg	
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	General population	inhalation	Acute/short term exposure - systemic effects		0,75 mg/m3	
Reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight <= 700) 25068-38-6	General population	inhalation	Long term exposure - systemic effects		0,75 mg/m3	
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	Workers	dermal	Long term exposure - systemic effects		104,15 mg/kg	
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	Workers	Inhalation	Long term exposure - systemic effects		29,39 mg/m3	
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	General population	dermal	Long term exposure - systemic effects		62,5 mg/kg	
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	General population	Inhalation	Long term exposure - systemic effects		8,7 mg/m3	
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	General population	oral	Long term exposure - systemic effects		6,25 mg/kg	
Reaction product: bisphenol-F-(epichlorhydrin); epoxy resin (number average molecular weight ≤ 700) (old)	Workers	dermal	Acute/short term exposure - local effects		8,3 µg/cm2	
Maleic anhydride 108-31-6	Workers	inhalation	Acute/short term exposure - systemic effects		0,8 mg/m3	
Maleic anhydride 108-31-6	Workers	inhalation	Acute/short term exposure - local effects		0,8 mg/m3	
Maleic anhydride	Workers	inhalation	Long term		0,4 mg/m3	

108-31-6			exposure - systemic effects			
Maleic anhydride 108-31-6	Workers	inhalation	Long term exposure - local effects		0,4 mg/m ³	

Biological Exposure Indices:

None

8.2. Exposure controls:

Engineering controls:

Ensure good ventilation/extraction.

Respiratory protection:

Ensure adequate ventilation.

An approved mask or respirator fitted with an organic vapour cartridge should be worn if the product is used in a poorly ventilated area

Filter type: A (EN 14387)

Hand protection:

Chemical-resistant protective gloves (EN 374).

Suitable materials for short-term contact or splashes (recommended: at least protection index 2, corresponding to > 30 minutes permeation time as per EN 374):

nitrile rubber (NBR; ≥ 0.4 mm thickness)

Suitable materials for longer, direct contact (recommended: protection index 6, corresponding to > 480 minutes permeation time as per EN 374):

nitrile rubber (NBR; ≥ 0.4 mm thickness)

This information is based on literature references and on information provided by glove manufacturers, or is derived by analogy with similar substances. Please note that in practice the working life of chemical-resistant protective gloves may be considerably shorter than the permeation time determined in accordance with EN 374 as a result of the many influencing factors (e.g. temperature). If signs of wear and tear are noticed then the gloves should be replaced.

Eye protection:

Safety glasses with sideshields or chemical safety goggles should be worn if there is a risk of splashing.

Protective eye equipment should conform to EN166.

Skin protection:

Wear suitable protective clothing.

Protective clothing should conform to EN 14605 for liquid splashes or to EN 13982 for dusts.

Advices to personal protection equipment:

The information provided on personal protective equipment is for guidance purposes only. A full risk assessment should be conducted prior to using this product to determine the appropriate personal protective equipment to suit local conditions.

Personal protective equipment should conform to the relevant EN standard.

SECTION 9: Physical and chemical properties**9.1. Information on basic physical and chemical properties**

Appearance

liquid

pasty

black

Odor

typical

Odour threshold

No data available / Not applicable

pH

No data available / Not applicable

Melting point

No data available / Not applicable

Solidification temperature

No data available / Not applicable

Initial boiling point

Polymerization may occur at elevated temperature.

Flash point

> 100 °C (> 212 °F)

Evaporation rate

No data available / Not applicable

Flammability	No data available / Not applicable
Explosive limits	No data available / Not applicable
Vapour pressure	No data available / Not applicable
Relative vapour density:	No data available / Not applicable
Density (20 °C (68 °F))	1,1 - 1,5 g/cm ³
Bulk density	No data available / Not applicable
Solubility	No data available / Not applicable
Solubility (qualitative) (20 °C (68 °F); Solvent: Water)	Not miscible or difficult to mix
Solubility (qualitative) (20 °C (68 °F); Solvent: ketones)	Partially miscible
Partition coefficient: n-octanol/water	No data available / Not applicable
Auto-ignition temperature	No data available / Not applicable
Decomposition temperature	No data available / Not applicable
Viscosity	No data available / Not applicable
Viscosity (kinematic)	No data available / Not applicable
Explosive properties	No data available / Not applicable
Oxidising properties	No data available / Not applicable

9.2. Other information

No data available / Not applicable

SECTION 10: Stability and reactivity**10.1. Reactivity**

Reacts with alcohols and amines.

Reacts with oxidants, acids and lyes

Polymerization may occur at elevated temperature or in the presence of incompatible materials.

10.2. Chemical stability

Stable under recommended storage conditions.

10.3. Possibility of hazardous reactions

See section reactivity

10.4. Conditions to avoid

Do not heat mixed adhesive unless you plan to use immediately.

Failure to observe these precautions may result in excessive heat build-up causing an exotherm.

Danger of decomposition if exposed to heat.

10.5. Incompatible materials

See section reactivity.

10.6. Hazardous decomposition products

Oxides of carbon and nitrogen, aldehydes, acids and undetermined organics.

Traces of

Toxic fluorine compounds.

Hydrogen fluoride

At higher temperature carbon oxides and nitrogen oxides may be generated.

May produce fumes when heated to decomposition. Fumes may contain carbon monoxide and other toxic fumes.

See section 5.

SECTION 11: Toxicological information

11.1. Information on toxicological effects

Acute oral toxicity:

The mixture is classified based on calculation method referring to the classified substances present in the mixture.

Hazardous substances CAS-No.	Value type	Value	Species	Method
reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	LD50	> 2.000 mg/kg	rat	OECD Guideline 420 (Acute Oral Toxicity)
Bisphenol F diglycidyl ether 39817-09-9	LD50	> 5.000 mg/kg	rat	
Bisphenol-F epichlorhydrin resin; MW<700	LD50	> 5.000 mg/kg	rat	OECD Guideline 401 (Acute Oral Toxicity)
1-Chloro-2,3-epoxypropane, polymer with polypropyleneglycol 9072-62-2	LD50	> 2.000 mg/kg	rat	not specified
Maleic anhydride 108-31-6	LD50	1.090 mg/kg	rat	OECD Guideline 401 (Acute Oral Toxicity)

Acute dermal toxicity:

The mixture is classified based on calculation method referring to the classified substances present in the mixture.

Hazardous substances CAS-No.	Value type	Value	Species	Method
reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	LD50	> 2.000 mg/kg	rat	OECD Guideline 402 (Acute Dermal Toxicity)
Bisphenol F diglycidyl ether 39817-09-9	LD50	> 6.000 mg/kg	rabbit	
Bisphenol-F epichlorhydrin resin; MW<700	LD50	> 2.000 mg/kg	rat	OECD Guideline 402 (Acute Dermal Toxicity)
1-Chloro-2,3-epoxypropane, polymer with polypropyleneglycol 9072-62-2	LD50	> 2.000 mg/kg	rat	not specified
Maleic anhydride 108-31-6	LD50	2.620 mg/kg	rabbit	not specified

Acute inhalative toxicity:

No data available.

Skin corrosion/irritation:

The mixture is classified based on calculation method referring to the classified substances present in the mixture.

Hazardous substances CAS-No.	Result	Exposure time	Species	Method
reaction product: bisphenol-A- (epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	moderately irritating	24 h	rabbit	Draize Test
Bisphenol-F epichlorhydrin resin; MW<700	irritating	4 h	rabbit	OECD Guideline 404 (Acute Dermal Irritation / Corrosion)
Maleic anhydride 108-31-6	highly irritating		rabbit	OECD Guideline 404 (Acute Dermal Irritation / Corrosion)

Serious eye damage/irritation:

The mixture is classified based on calculation method referring to the classified substances present in the mixture.

Hazardous substances CAS-No.	Result	Exposure time	Species	Method
reaction product: bisphenol-A- (epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	not irritating		rabbit	OECD Guideline 405 (Acute Eye Irritation / Corrosion)
Bisphenol-F epichlorhydrin resin; MW<700	not irritating		rabbit	OECD Guideline 405 (Acute Eye Irritation / Corrosion)
Maleic anhydride 108-31-6	corrosive		rabbit	OECD Guideline 405 (Acute Eye Irritation / Corrosion)

Respiratory or skin sensitization:

The mixture is classified based on threshold limits referring to the classified substances present in the mixture.

Hazardous substances CAS-No.	Result	Test type	Species	Method
reaction product: bisphenol-A- (epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	sensitising	Mouse local lymphnode assay (LLNA)	mouse	OECD Guideline 429 (Skin Sensitisation: Local Lymph Node Assay)
Bisphenol-F epichlorhydrin resin; MW<700	sensitising	Mouse local lymphnode assay (LLNA)	mouse	OECD Guideline 429 (Skin Sensitisation: Local Lymph Node Assay)
Maleic anhydride 108-31-6	sensitising	Guinea pig maximisation test	guinea pig	OECD Guideline 406 (Skin Sensitisation)

Germ cell mutagenicity:

The mixture is classified based on threshold limits referring to the classified substances present in the mixture.

Hazardous substances CAS-No.	Result	Type of study / Route of administration	Metabolic activation / Exposure time	Species	Method
reaction product: bisphenol-A- (epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	negative	bacterial reverse mutation assay (e.g Ames test)	with and without		OECD Guideline 472 (Genetic Toxicology: Escherichia coli, Reverse Mutation Assay)
Bisphenol-F epichlorhydrin resin; MW<700	positive	bacterial reverse mutation assay (e.g Ames test)	with and without		OECD Guideline 471 (Bacterial Reverse Mutation Assay)
Maleic anhydride 108-31-6	negative	bacterial reverse mutation assay (e.g Ames test)	with and without		OECD Guideline 471 (Bacterial Reverse Mutation Assay)
reaction product: bisphenol-A- (epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	negative	oral: gavage		mouse	not specified
Bisphenol-F epichlorhydrin resin; MW<700	negative	oral: gavage		mouse	OECD Guideline 474 (Mammalian Erythrocyte Micronucleus Test)
Bisphenol-F epichlorhydrin resin; MW<700	negative	oral: gavage		rat	OECD Guideline 486 (Unscheduled DNA Synthesis (UDS) Test with Mammalian Liver Cells in vivo)
Maleic anhydride 108-31-6	negative	inhalation		rat	OECD Guideline 475 (Mammalian Bone Marrow Chromosome Aberration Test)

Carcinogenicity

The mixture is classified based on threshold limits referring to the classified substances present in the mixture.

Hazardous components CAS-No.	Result	Route of application	Exposure time / Frequency of treatment	Species	Sex	Method
reaction product: bisphenol-A- (epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	not carcinogenic	dermal	2 y daily	mouse	male	OECD Guideline 453 (Combined Chronic Toxicity / Carcinogenicity Studies)
reaction product: bisphenol-A- (epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	not carcinogenic	oral: gavage	2 y daily	rat	male/female	OECD Guideline 453 (Combined Chronic Toxicity / Carcinogenicity Studies)

Reproductive toxicity:

The mixture is classified based on threshold limits referring to the classified substances present in the mixture.

Hazardous substances CAS-No.	Result / Value	Test type	Route of application	Species	Method
reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	NOAEL P >= 50 mg/kg NOAEL F1 >= 750 mg/kg NOAEL F2 >= 750 mg/kg	Two generation study	oral: gavage	rat	OECD Guideline 416 (Two-Generation Reproduction Toxicity Study)
Bisphenol-F epichlorhydrin resin; MW<700	NOAEL P > 750 mg/kg NOAEL F1 750 mg/kg NOAEL F2 750 mg/kg	two-generation study	oral: gavage	rat	OECD Guideline 416 (Two-Generation Reproduction Toxicity Study)
Maleic anhydride 108-31-6	NOAEL P 55 mg/kg NOAEL F1 55 mg/kg	Two generation study	oral: gavage	rat	OECD Guideline 416 (Two-Generation Reproduction Toxicity Study)

STOT-single exposure:

No data available.

STOT-repeated exposure::

The mixture is classified based on threshold limits referring to the classified substances present in the mixture.

Hazardous substances CAS-No.	Result / Value	Route of application	Exposure time / Frequency of treatment	Species	Method
reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	NOAEL 50 mg/kg	oral: gavage	14 w daily	rat	OECD Guideline 408 (Repeated Dose 90-Day Oral Toxicity in Rodents)
Bisphenol-F epichlorhydrin resin; MW<700	NOAEL 250 mg/kg	oral: gavage	13 w daily	rat	OECD Guideline 408 (Repeated Dose 90-Day Oral Toxicity in Rodents)
Maleic anhydride 108-31-6	NOAEL 40 mg/kg	oral: feed	90 d daily	rat	not specified

Aspiration hazard:

No data available.

SECTION 12: Ecological information

General ecological information:

If used properly the product does not enter the drains.

In the cured state contribution of this product to Environmental Hazards is insignificant in comparison to articles in which it is used.

Do not empty into drains / surface water / ground water.

12.1. Toxicity

Toxicity (Fish):

The mixture is classified based on calculation method referring to the classified substances present in the mixture.

Hazardous substances CAS-No.	Value type	Value	Exposure time	Species	Method
reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight \leq 700) 25068-38-6	LC50	1,75 mg/l	96 h	Oncorhynchus mykiss	OECD Guideline 203 (Fish, Acute Toxicity Test)
Bisphenol F diglycidyl ether 39817-09-9	LC50	> 1 - 10 mg/l	96 h	not specified	OECD Guideline 203 (Fish, Acute Toxicity Test)
Bisphenol-F epichlorhydrin resin; MW<700	LC50	5,7 mg/l	96 h	Leuciscus idus	OECD Guideline 203 (Fish, Acute Toxicity Test)
1-Chloro-2,3-epoxypropane, polymer with polypropyleneglycol 9072-62-2	LC50	67 mg/l	96 h	Leuciscus idus	OECD Guideline 203 (Fish, Acute Toxicity Test)
Maleic anhydride 108-31-6	LC50	115 mg/l			OECD Guideline 203 (Fish, Acute Toxicity Test)

Toxicity (Daphnia):

The mixture is classified based on calculation method referring to the classified substances present in the mixture.

Hazardous substances CAS-No.	Value type	Value	Exposure time	Species	Method
reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight \leq 700) 25068-38-6	EC50	1,7 mg/l	48 h	Daphnia magna	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)
Bisphenol F diglycidyl ether 39817-09-9	EC50	> 1 - 10 mg/l	48 h	Daphnia magna	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)
Bisphenol-F epichlorhydrin resin; MW<700	EC50	2,55 mg/l	48 h	Daphnia magna	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)
Maleic anhydride 108-31-6	EC50	42,81 mg/l	48 h	Daphnia magna	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)

Chronic toxicity to aquatic invertebrates

The mixture is classified based on calculation method referring to the classified substances present in the mixture.

Hazardous substances CAS-No.	Value type	Value	Exposure time	Species	Method
reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight \leq 700) 25068-38-6	NOEC	0,3 mg/l	21 d	Daphnia magna	OECD 211 (Daphnia magna, Reproduction Test)
Bisphenol-F epichlorhydrin resin; MW<700	NOEC	0,3 mg/l	21 d	Daphnia magna	OECD 211 (Daphnia magna, Reproduction Test)

Toxicity (Algae):

The mixture is classified based on calculation method referring to the classified substances present in the mixture.

Hazardous substances CAS-No.	Value type	Value	Exposure time	Species	Method
reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	EC50	> 11 mg/l	72 h	Scenedesmus capricornutum	OECD Guideline 201 (Alga, Growth Inhibition Test)
reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	NOEC	4,2 mg/l	72 h	Scenedesmus capricornutum	OECD Guideline 201 (Alga, Growth Inhibition Test)
Bisphenol-F epichlorhydrin resin; MW<700	EC50	1,8 mg/l	72 h	Pseudokirchneriella subcapitata	OECD Guideline 201 (Alga, Growth Inhibition Test)
Maleic anhydride 108-31-6	EC50	29 mg/l	72 h	Scenedesmus subspicatus (new name: Desmodesmus subspicatus)	OECD Guideline 201 (Alga, Growth Inhibition Test)
Maleic anhydride 108-31-6	EC10	23 mg/l	72 h	Scenedesmus subspicatus (new name: Desmodesmus subspicatus)	OECD Guideline 201 (Alga, Growth Inhibition Test)

Toxicity to microorganisms

The mixture is classified based on calculation method referring to the classified substances present in the mixture.

Hazardous substances CAS-No.	Value type	Value	Exposure time	Species	Method
reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	IC50	> 100 mg/l	3 h	activated sludge, industrial	other guideline:
Bisphenol-F epichlorhydrin resin; MW<700	IC50	> 100 mg/l	3 h	activated sludge, industrial	other guideline:
Maleic anhydride 108-31-6	EC0	> 10.000 mg/l	30 min		not specified

12.2. Persistence and degradability

The product is not biodegradable.

Hazardous substances CAS-No.	Result	Test type	Degradability	Exposure time	Method
reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	not readily biodegradable.	aerobic	5 %	28 d	OECD Guideline 301 F (Ready Biodegradability: Manometric Respirometry Test)
Bisphenol F diglycidyl ether 39817-09-9	not readily biodegradable.	aerobic	< 10 %	28 d	OECD 301 A - F
Bisphenol-F epichlorhydrin resin; MW<700	not readily biodegradable.	aerobic	0 %	28 d	OECD Guideline 301 D (Ready Biodegradability: Closed Bottle Test)
Maleic anhydride 108-31-6	readily biodegradable	aerobic	98 %	7 d	OECD Guideline 301 E (Ready biodegradability: Modified OECD Screening Test)

12.3. Bioaccumulative potential

No data available.

No substance data available.

12.4. Mobility in soil

Cured adhesives are immobile.

Hazardous substances CAS-No.	LogPow	Temperature	Method
reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	3,242	25 °C	EU Method A.8 (Partition Coefficient)
Bisphenol-F epichlorhydrin resin; MW<700	2,7 - 3,6		OECD Guideline 117 (Partition Coefficient (n-octanol / water), HPLC Method)
Maleic anhydride 108-31-6	1,62		not specified

12.5. Results of PBT and vPvB assessment

Hazardous substances CAS-No.	PBT / vPvB
reaction product: bisphenol-A-(epichlorhydrin); epoxy resin (number average molecular weight≤700) 25068-38-6	Not fulfilling Persistent, Bioaccumulative and Toxic (PBT), very Persistent and very Bioaccumulative (vPvB) criteria.
Bisphenol-F epichlorhydrin resin; MW<700	Not fulfilling Persistent, Bioaccumulative and Toxic (PBT), very Persistent and very Bioaccumulative (vPvB) criteria.
Maleic anhydride 108-31-6	Not fulfilling Persistent, Bioaccumulative and Toxic (PBT), very Persistent and very Bioaccumulative (vPvB) criteria.

12.6. Other adverse effects

No data available.

SECTION 13: Disposal considerations

13.1. Waste treatment methods

Product disposal:

Special waste incineration with the approval of the responsible local authority.

Disposal of uncleaned packages:

Disposal must be made according to official regulations.

Use packages for recycling only when totally empty.

Packaging that cannot be cleaned are to be disposed of in the same manner as the product.

Waste code

08 04 09 waste adhesives and sealants containing organic solvents and other dangerous substances

The valid EWC waste code numbers are source-related. The manufacturer is therefore unable to specify EWC waste codes for the articles or products used in the various sectors. The EWC codes listed are intended as a recommendation for users. We will be happy to advise you.

SECTION 14: Transport information
--

14.1. UN number

ADR	3082
RID	3082
ADN	3082
IMDG	3082
IATA	3082

14.2. UN proper shipping name

ADR	ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S. (Epoxy resin)
RID	ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S. (Epoxy resin)
ADN	ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S. (Epoxy resin)
IMDG	ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S. (Epoxy resin)
IATA	Environmentally hazardous substance, liquid, n.o.s. (Epoxy resin)

14.3. Transport hazard class(es)

ADR	9
RID	9
ADN	9
IMDG	9
IATA	9

14.4. Packing group

ADR	III
RID	III
ADN	III
IMDG	III
IATA	III

14.5. Environmental hazards

ADR	not applicable
RID	not applicable
ADN	not applicable
IMDG	Marine pollutant
IATA	not applicable

14.6. Special precautions for user

ADR	not applicable Tunnelcode:
RID	not applicable
ADN	not applicable
IMDG	not applicable
IATA	not applicable

The transport classifications in this section apply generally to packed and bulk goods alike. For containers with a net volume of no more than 5 L for liquid substances or a net mass of no more than 5 kg for solid substances per individual or inner package, the exemptions SP 375 (ADR), 197 (IATA), 969 (IMDG) may be applied, which can result in a deviation from the transport classification for packed goods.

14.7. Transport in bulk according to Annex II of Marpol and the IBC Code

not applicable

SECTION 15: Regulatory information**15.1. Safety, health and environmental regulations/legislation specific for the substance or mixture**

VOC content < 3 %
(2010/75/EC)

15.2. Chemical safety assessment

A chemical safety assessment has not been carried out.

SECTION 16: Other information

The labelling of the product is indicated in Section 2. The full text of all abbreviations indicated by codes in this safety data sheet are as follows:

H302 Harmful if swallowed.
H314 Causes severe skin burns and eye damage.
H315 Causes skin irritation.
H317 May cause an allergic skin reaction.
H318 Causes serious eye damage.
H319 Causes serious eye irritation.
H334 May cause allergy or asthma symptoms or breathing difficulties if inhaled.
H372 Causes damage to organs through prolonged or repeated exposure if inhaled.
H411 Toxic to aquatic life with long lasting effects.
H412 Harmful to aquatic life with long lasting effects.

Further information:

This Safety Data Sheet has been produced for sales from Henkel to parties purchasing from Henkel, is based on Regulation (EC) No 1907/2006 and provides information in accordance with applicable regulations of the European Union only. In that respect, no statement, warranty or representation of any kind is given as to compliance with any statutory laws or regulations of any other jurisdiction or territory other than the European Union. When exporting to territories other than the European Union, please consult with the respective Safety Data Sheet of the concerned territory to ensure compliance or liaise with Henkel's Product Safety and Regulatory Affairs Department (ua-productsafety.de@henkel.com) prior to export to other territories than the European Union.

This information is based on our current level of knowledge and relates to the product in the state in which it is delivered. It is intended to describe our products from the point of view of safety requirements and is not intended to guarantee any particular properties.

Relevant changes in this safety data sheet are indicated by vertical lines at the left margin in the body of this document. Corresponding text is displayed in a different color on shadowed fields.