

LOCTITE HYSOL GR 21F-02

July 2012

PRODUCT DESCRIPTION

LOCTITE HYSOL GR 21F-02 provides the following product characteristics:

Technology	Epoxy
Appearance	Black
Cure	Heat cure
Product Benefits	<ul style="list-style-type: none"> • Green product • High moldability
Filler Weight, %	72
Typical Package Application	Bridge Package and Axial Package
Application	Molding compound
Flammability	94 V-0

LOCTITE HYSOL GR 21F-02 epoxy molding compound delivers outstanding performance and ease of use. LOCTITE HYSOL GR 21F-02 is ECN base green molding compound suitable for medium voltage applications.

LOCTITE HYSOL GR 21F-02 meets UL 94 V-0 Flammability at 6.35mm thickness.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Gel Time @ 175 °C, seconds	16
Spiral Flow, @ 175°C, cm	55.88
Shelf Life:	
@ 5°C, days	365
Hot Hardness, Shore-D @ 175°C, 90 seconds	85

TYPICAL PROCESS DATA

Handling	
Preheat Temperature, °C	77 to 94
Molding Temperature, °C	160 to 190
Transfer Pressure, psi	500 to 1,500
Transfer Time:	
Conventional mold, seconds	15 to 25
Automold, seconds	12 to 20
Curing Time, :	
Conventional mold:	
@ 175°C, seconds	70 to 90
Automold:	
@ 175°C, seconds	50 to 70
Post Cure @ 175°C, hours	2 to 6

LOCTITE HYSOL GR 21F-02 has been formulated to provide the best possible moldability and as wide a molding latitude as possible. Although molding and curing conditions will vary from situation to situation, recommended starting ranges are shown above.

TYPICAL PROPERTIES OF CURED MATERIAL

All measurements taken at 25 °C unless otherwise noted. All physical, electrical and analytical measurements taken on specimens cured for 2 minutes @ 175 °C with post cure of 6 hours at 175 °C, unless otherwise specified.

Physical Properties:

Coefficient of Thermal Expansion, ppm/°C:	
Below Tg	19
Above Tg	62
Glass Transition Temperature, °C	180
Specific Gravity	1.78
Molded shrinkage, as molded, %	0.21
Flexural Strength Kg/mm ² :	
@ 25 °C	12
Flexural Modulus Kg/mm ² :	
@ 25 °C	1,400
Thermal Conductivity, W/(m-K)	0.65
Water Extract Data, 90 min water boil:	
Conductivity, micro mhos	2.0
pH of extract	6.0
Extractable Ionic Content, ppm:	
Chloride (Cl ⁻)	2
Sodium (Na ⁺)	1

Electrical Properties:

Volume Resistivity, ohms-cm, 500 volts:	
@ 21°C	10×10 ¹⁵

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Powder Storage - Powder or preforms should be stored at 5°C or below, in closed containers. After removal from cold storage, the material **MUST** be allowed to come to room temperature, in the sealed container, to avoid moisture contamination. The suggested waiting time for a standard 15 kg carton box is 24 hours.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
kV/mm $\times 25.4 = \text{V/mil}$
mm / 25.4 = inches
N $\times 0.225 = \text{lb}$
N/mm $\times 5.71 = \text{lb/in}$
N/mm² $\times 145 = \text{psi}$
MPa $\times 145 = \text{psi}$
N·m $\times 8.851 = \text{lb·in}$
N·m $\times 0.738 = \text{lb·ft}$
N·mm $\times 0.142 = \text{oz·in}$
mPa·s = cP

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the

product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.2